

# SOPRASEAL STICK PRIMER

TECHNICAL DATA SHEET 250730SCANE

(supersedes 170829SCANE)



ACCESSORIES PRODUCTS

APPLICATIONS

WALLS

## DESCRIPTION

SOPRASEAL STICK PRIMER is a primer specifically designed to enhance the adhesion of self-adhesive membranes on porous surfaces such as exterior gypsum boards at temperatures above -30 °C (-22 °F) for an application with a brush or a roll, and above -10 °C (14 °F) for an application with a spray equipment. It is composed of SBS synthetic rubbers, adhesive enhancing resins and volatile solvents.

## RECOMMENDED SUBSTRATES

This product can be used on exterior gypsum boards, wood, metal and concrete.

## APPLICATION

SOPRASEAL STICK PRIMER can be applied with a brush, a roll or spray equipment on dry and clean substrates. It must be well shaken before use and must be thoroughly dry before applying the waterproofing membrane.

**Warning:** Keep away from all flame or spark sources when SOPRASEAL STICK PRIMER is drying.

FOR COMPLETE INFORMATION ON PRODUCT APPLICATION, PLEASE CONSULT YOUR SOPREMA REPRESENTATIVE.

## GENERAL INFORMATION

| Specifications                                              | SOPRASEAL STICK PRIMER                   |                                                                            |
|-------------------------------------------------------------|------------------------------------------|----------------------------------------------------------------------------|
| Physical state                                              | Liquid                                   |                                                                            |
| Colour                                                      | Orange                                   |                                                                            |
| Specific gravity,<br>at 20 °C (68 °F)                       | 0.79 kg/L (6.59 lb/US gal)               |                                                                            |
| Coverage applied with<br>a brush or a roll <sup>(1)</sup> , | <i>Porous surface</i>                    | 0.3 to 0.5 L/m <sup>2</sup> (0.736 to 1.227 US gal/100 ft <sup>2</sup> )   |
|                                                             | <i>Non-porous surface</i>                | 0.1 to 0.25 L/m <sup>2</sup> (0.245 to 0.614 US gal/100 ft <sup>2</sup> )  |
| Coverage applied with<br>a spray equipment <sup>(1)</sup> , | <i>Porous surface</i>                    | 0.15 to 0.21 L/m <sup>2</sup> (0.368 to 0.515 US gal/100 ft <sup>2</sup> ) |
|                                                             | <i>Non-porous surface</i>                | 0.07 to 0.1 L/m <sup>2</sup> (0.172 to 0.245 US gal/100 ft <sup>2</sup> )  |
| Containers                                                  | 19 L (5.0 US gal)<br>3.78 L (1.0 US gal) |                                                                            |

(1): The coverage is approximative and may vary depending on the substrate condition and the application technique.



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH

# SOPRASEAL STICK PRIMER

TECHNICAL DATA SHEET 250730SCANE

(supersedes 170829SCANE)



ACCESSORIES PRODUCTS

APPLICATIONS

WALLS

## PROPERTIES

| Properties                                            | SOPRASEAL STICK PRIMER                                          |
|-------------------------------------------------------|-----------------------------------------------------------------|
| Solids by weight                                      | 24%                                                             |
| Viscosity, Brookfield,<br>at 25°C (77°F)              | 200 cP                                                          |
| Drying time for application with<br>a brush or a roll | 15 to 60 minutes, depending on temperature and quantity applied |
| Drying time for application with<br>a spray equipment | 5 to 10 minutes, depending on temperature and quantity applied  |

(All values are nominal)

## CLEANING

Tools and equipments can be cleaned with petroleum solvents such as mineral sprits, Varsol, Xylene, etc.

## STORAGE AND HANDLING

SOPRASEAL STICK PRIMER can be kept sixty (60) months when properly stored in its original sealed containers. Store in a well ventilated area, away from any source of heat, dampness, humidity, oxidizing agents or direct sunlight. Flammable before curing. Keep away from sources of ignition.

FOR MORE INFORMATION, REFER TO THE INSTRUCTIONS ON THE LABEL AND RELEVANT SAFETY DATA SHEET (SDS).



SOPREMA.US • 1.800.356.3521

SOPREMA.CA • 1.877.MAMMOUTH